


FC grade

Key Word		Product Name	
Test File Name	box5 03-18-J-010-04 JCMethod	File Name	peeltestwith.glass.lmax
Report Date	2018/10/18	Test Date	2018/10/18
Test Type	Peel	Speed	300mm/min
Shape	Plate1	No of Batches:	1
Qty/Batch:	5		

Name	Thickness	Weight
Unit	mm	gf
1_1	10.0000	1.0000
1_2	10.0000	1.0000
1_3	10.0000	1.0000
1_4	10.0000	1.0000
1_5	10.0000	1.0000

Name	All_Mean_Force
Parameters	
Unit	N
1_1	28.0250
1_2	28.4504
1_3	33.6467
1_4	35.4200
1_5	32.2123

Average = 31.55 N/10




Spectrum Point Pick Report

11/08/2018 04:13:51 AM

Data Set: o3-18-k-011-02-box26 - RawData

FC grade



[Measurement Properties]
 Wavelength Range (nm.): 200.00 to 800.00
 Scan Speed: Fast
 Sampling Interval: 5.0
 Auto Sampling Interval: Disabled
 Scan Mode: Auto

No.	Wavelength	Transmittan	Description
1	300.00	0.009	
2			

[Instrument Properties]
 Instrument Type: UV-2600 Series
 Measuring Mode: Transmittance
 Slit Width: 2.0
 Accumulation time: 2.0 sec.
 Light Source Change Wavelength: 323.0 nm
 Detector Unit: External(2Detector)
 Detector Change Wavelength: 870.0 nm
 S/R Exchange: Normal
 Stair Correction: OFF

[Attachment Properties]
 Attachment: None

[Operation]
 Threshold: 0.0010000
 Points: 4
 InterPolate: Disabled
 Average: Disabled

[Sample Preparation Properties]
 Weight:
 Volume:
 Dilution:
 Path Length:
