


Key Word	Product Name		
Test File Name	UFC-18-G-004-08 B64	Method File Name	peeltest.with.glass.lmax
Report Date	2018/07/25	Test Date	2018/07/25
Test Type	Peel	Speed	300mm/min
Shape	Plate1	No of Batches:	1
Qty/Batch:	5		

Name	Thickness	Weight
Unit	mm	gf
1_1	10.0000	1.0000
1_2	10.0000	1.0000
1_3	10.0000	1.0000
1_4	10.0000	1.0000
1_5	10.0000	1.0000

Name	All_Mean_Force
Parameters	
Unit	N
1_1	29.9006
1_2	30.1001
1_3	31.2331
1_4	30.9009
1_5	33.2663




Spectrum Point Pick Report

07/24/2018 11:56:33 PM

Data Set: **ufc-18-g-004-08** jc270-h box64 - RawData

ufc.grade



[Measurement Properties]
Wavelength Range (nm.): 200.00 to 800.00
Scan Speed: Fast
Sampling Interval: 5.0
Auto Sampling Interval: Disabled
Scan Mode: Auto

No.	Wavelength	Transmittan	Description
1	300.00	0.004	
2			

[Instrument Properties]
Instrument Type: UV-2600 Series
Measuring Mode: Transmittance
Slit Width: 2.0
Accumulation time: 2.0 sec.
Light Source Change Wavelength: 323.0 nm
Detector Unit: External(2Detector)
Detector Change Wavelength: 870.0 nm
S/R Exchange: Normal
Stair Correction: OFF

[Attachment Properties]
Attachment: None

[Operation]
Threshold: 0.0010000
Points: 4
InterPolate: Disabled
Average: Disabled

[Sample Preparation Properties]
Weight:
Volume:
Dilution:
Path Length:
.....